



TULSI - 069 HT

Doc. No.: CHCL-6

Issue No.: 03

Issue Date: 17.11.2015

Replaces: All Previous Issues

PHYSIOCHEMICAL PROPERTIES

PROPERTY	UNIT	TULSI-069-HT
Whiteness	%	92-96
Average Particle size	micron	2.0 max
Surface Area	m ² /gm	6-8
Specific Gravity	-	2.7 - 2.8
Bulk Density	gm/cc	0.40 - 0.50
Water Absorption	%	60-65
pH Value	-	5.5 - 6.5
Moisture	% max	0.2
Water Soluble	%	Nil
SiO ₂	%	50-52
Al ₂ O ₂	% max	45-47
Fe ₂ O ₃	% max	0.50
Mixed Oxides	% max	1.0
Loss on Ignition Loss	% max	0.50
Residue on 500 mesh	%	0.20
Packing	kgs/bag	25

* At the time of packing

This information and our technical advice-whether verbal, in writing or by way of trials are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sales and Delivery.

Correspondence Address :

111/230, Harsh Nagar
KANPUR - 208 012. (INDIA)
Ph. :0512-2555292
Website: www.mlagroup.com
Email: info@mlagroup.com

CERTIFICATIONS

